



MANUFACTURER: SECCO HCSP GROUP JSC

81A , Street 8, Linh Trung , Thu Duc ,
Ho Chi Minh City , Vietnam

T:+84909075959
tranhien3839@gmail.com

Tax code: 0312025426



www.seccoamericas.com

HEADOFFICE: SECCO AMERICAS, LLC

4500 Biscayne Blvd, Penthouse North,
Miami, FL 33137, USA.

T:+1.786.548.2948
orders@seccoamericas.com

SPECIFICATION OF DF-1 PACKING MATERIAL

TEST TIME: 2020.9.18

Name	SECCO	METHOD	DF_1							
LOT NUMBER	JS20090501		TNK30//TQPE25//PTF20//NKZ30							
TEST ITEM	MEASUREMENT	TEST STANDARD	STANDARDS	VALUES					RESULT	
<input type="checkbox"/> APPEARANCE	—	Q/FXDB 01-2010	OK	OK	OK	OK	OK	OK	PASS	
<input type="checkbox"/> GSM	g/m ²	Q/FXDB 01-2010	100±6	106	105	103	105	105	PASS	
<input type="checkbox"/> WIDTH	mm	Q/FXDB 01-2010	110±1	110	110	110	110	110	PASS	
<input type="checkbox"/> SEAL STRENGTH	kgf/15mm	QB/T 2358-98	≥0.6	1.23	1.24	1.11	1.52	1.32	PASS	
<input type="checkbox"/> PULL STRENGTH	TD	kgf/15mm	GB/T 13022-91	≥2.5	4.35	4.36	4.26	4.33	4.58	PASS
	MD			≥2.5	7.65	8.1	7.88	7.64	7.54	PASS
<input type="checkbox"/> percentage elongation	TD	%	GB/T 13022-91	≥1.5	56.3	60.3	58.5	60.2	58.7	PASS
	MD			≥1.5	44.3	42.6	42.1	45.3	44.2	PASS
<input type="checkbox"/> peel strength	Peel1	Kgf/15mm	GB 8808-88	≥0.05	0.1	0.08	0.11	0.09	0.07	PASS
	Peel2			≥0.05	0.08	0.1	0.07	0.09	0.07	PASS
<input type="checkbox"/> PITCH	mm	Q/FXDB 01-2010							PASS	
<input type="checkbox"/> WVTR	s	Q/FXDB 01-2010	≤1500	380	430	700	720	500	PASS	
<input type="checkbox"/> Total residual solvents	mg/m ²	GB/T5009	≤5	0.46					PASS	
<input type="checkbox"/> Benzene residues	mg/m ²	GB/T5009	≤0	0					PASS	
<input type="checkbox"/> Hygienic performance	—	GB 9683—88	MEET STANDARD	MEET	MEET	MEET	MEET	MEET	PASS	
FINAL SLOUTION	PASS									